

**Coating binder, esp. for overcoating(s) for vehicles**

**Patent number:** DE4445355  
**Publication date:** 1996-06-27  
**Inventor:** BREMER GERHARD DIPL CHEM DR (DE); KERBER HERMANN DIPL CHEM (DE); KRUMME MANFRED (DE); LEY OLAF (DE); STEPHAN WERNER DIPL ING (DE)  
**Applicant:** HERBERTS GMBH (DE)  
**Classification:**  
**- international:** C08L33/02; C08L33/08; C08L33/14; C08J3/24; C08K5/29; C09D133/02; C09D133/08; C09D133/14; C08F220/10; C08F220/32; C08F2/06; C09D133/00; C09D133/14; C09D133/06; C09D133/02; C09D125/02; C08F220/26; C08F220/18; C08F220/04; C08F212/06; C08F212/08  
**- european:** C08F220/32; C08G18/62G6D; C08G18/62G6K  
**Application number:** DE19944445355 19941220  
**Priority number(s):** DE19944445355 19941220

**Report a data error here**

**Abstract of DE4445355**

A binder for (non)-aq. coatings is a copolymer, with COOH content corresp. to 25-50 mg KOH/g, obtd. by copolymerising (a) 20-35 wt.% of a glycidyl ester of an alpha , alpha -dialkyl substd. branched, aliphatic, satd. monocarboxylic acid, (b) 15-20% of a hydroxyalkyl ester of (meth)acrylic acid, (c) 10-40% of an alkyl ester of (meth)acrylic acid, (d) 8-25% of (meth)acrylic acid, and 20-35% of styrene and/or a styrene deriv. Pref. the binder contains an organic solvent. The COOH gps. are (partly) neutralised. A coating compsn. contains (A) the copolymer, (B) a polyisocyanate in amt. to give 0.5-2 NCO gps. w.r.t. 1 OH gp. in (A), (C) an organic solvent and/or water, and opt. (D) pigments, fillers and lacquer additives. The coating is prepd. by mixing the components (A)-(D).

---

Data supplied from the esp@cenet database - Worldwide